

FABRAL COLOR	SR	IE	SRI	STEEL			ALUMINUM			
				24GA.†	22GA.†	18GA.†	.032"†	.040"†	.050"†	.063"†
Regal White	.68	.86	82	●■▲◆	●	●	●■			●
Bone White	.72	.84	87	●	●	●	●	●	●	
Almond	.63	.86	75	●			●	●		
Sandstone	.54	.86	63	●■▲◆	●		●	●	●	
Surrey Beige	.40	.86	43	●◆	●		●	●	●	
Sierra Tan	.35	.86	37	●			●	●		
Medium Bronze	.30	.87	31	●■◆	●	●	●	●	●	●
Mansard Brown	.29	.86	29	●			●	●	●	
Dark Bronze	.26	.84	24	●■▲◆	●	●	●■	●	●	●
Matte Black	.27	.86	26	●	●		●	●		
Stone Gray	.36	.84	37	●			●			
Slate Gray	.37	.86	39	●◆			●	●		
Charcoal	.32	.85	32	●	●		●	●		
Slate Blue	.26	.85	24	●			●			
Regal Blue	.28	.86	27	●			●			
Patina Green	.29	.87	29	●			●			
Classic Green	.26	.84	24	●■	●		●	●		
Hartford Green	.10	.82	2	●			●			
Brandywine	.26	.85	24	●			●			
Colonial Red	.34	.86	35	●			●			
Pewter	.36	.85	38	●			●			
Bright Silver	.60	.77	68	●			●■			
Silversmith	.53	.78	59	●			●			
Champagne	.37	.83	38	●			●			
Bright Copper	.49	.85	55	●■			●■			

PAINT PERFORMANCE PROPERTIES	HOT DIPPED GALVANIZED STEEL OR GALVALUME®	ALUMINUM
<b>Accelerated Weathering</b> ASTM D 4587 (Drew Cycle Weatherometer)  ASTM G 23	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max  Hours: 5,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max  Hours: 5,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max
<b>Salt Spray</b> ASTM B 117	Hours: 1,000 Total Scribe: Rating 7 1/16" (1.6mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
<b>Humidity</b> ASTM D 2247	Hours: 2,000 Total Rating: 10, no blisters	Hours: 3,000 Total Rating: 10, no blisters
<b>Formability</b> ASTM D 4145	0T-3T	0T-3T
<b>ASTM D 522</b> (Elongation over 1/8" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
<b>Pencil Hardness</b> ASTM D 3363	HB-2H	HB-2H
<b>Abrasion Resistance</b> ASTM D 968	55-75 Liters of falling sand	55-75 Liters of falling sand
<b>Specular Gloss</b> ASTM D 523	20-35 at 60°	20-35 at 60°
<b>Reverse Impact</b> ASTM D 2794	2 x Metal thickness in inch-lbs. No loss of adhesion	1 1/2 x Metal thickness in inch-lbs. No loss of adhesion
<b>Flame Test</b> ASTM E 84	Class A rated coating	Class A rated coating

- † Standard Coil Width is 48.25"  
‡ Standard Coil Width is 44.375"  
● Available in Standard Coil Width.  
■ Available in 40.25" Coil Width.  
▲ Available in 38" Coil Width.  
◆ Available in 44.375" Coil Width.

**Notes on availability:**

- 24ga, .032", .040", .050" & .063" are standard 48.25" in width, 22ga & 18ga are 44.375" in width for painted items.
- Standard inventory is non-embossed. Please contact us for the availability of stucco embossing.
- Protective strippable film is available upon request.
- Metallic/Mica colors are subject to premium pricing.
- Subject to change without notice.
- Unpainted, acrylic coated, Aluminum-Zinc Alloy steel (AZ-55) is maintained in: 26ga x 20", 26ga x 28", 26ga x 48.25", 24ga x 20", 24ga x 24", 24ga x 28", 24ga x 48.25", 22ga x 44.375", 22ga x 48.25", 20ga x 44.375" and 18ga x 44.375".
- All colors are supplied in Medium Gloss (20-35 at 60°). Low Gloss available subject to minimum coating run.

Fabra's standard architectural colors and finishes feature 70% polyvinylidene fluoride (PVDF) resin paint systems to ensure long term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set up charges may apply. Consult [www.fabrai.com](http://www.fabrai.com) for additional information.

**Kynar®**